

Release Notification Date: 01/24/2023

SPM 70-21-06 CLEANING METHOD NO. 6 - HEAVY-DUTY ALKALINE CLEANER (WITHOUT INHIBITED PHOSPHORIC ACID)

### DISCLAIMER

The Incremental Changes published by GE Aviation are considered Instructions for Continued Airworthiness. These Incremental Changes, along with the current Manual revision and published Temporary Revisions, constitute the latest Instructions for Continued Airworthiness.

## GE Designated: -CONFIDENTIAL-

The information contained in this document is GE proprietary information and is disclosed in confidence. It is the property of GE and shall not be used, disclosed to others or reproduced without the express written consent of GE, including, but without limitation, it is not to be used in the creation, manufacture, development, or derivation of any repairs, modifications, spare parts, designs, or configuration changes or to obtain FAA or any other government or regulatory approval to do so. If consent is given for reproduction in whole or in part, this notice and the notice set forth on each page of this document shall appear in any such reproduction in whole or part.

This technical data is considered subject to the Export Administration Regulations (EAR) pursuant to 15 CFR Parts 730-774. Transfer of this data by any means to a Non-U.S. Person, whether in the United States or abroad, without the proper U.S. Government authorization (e.g., License, exemption, NLR, etc.), is strictly prohibited.

Copyright (2023) General Electric Company, U.S.A.

# **HIGHLIGHTS**

HIGHLIGHT	REFERENCE	DESCRIPTION	ON OF C	<u>CHANGE</u>			
		Toghnigal	Chango	. 7.ddod	Millonnium	colution	dai

sk70-21-06-110-042 Technical Change: Added Millennium solution data to the Alkaline Degreasing/Rust Removing Solution table.

tk70-21-06-110-004 Technical Change: Added CAUTION and NOTE statement to the General section.

TASK 70-21-06-110-004

1. General.

CAUTION: DO NOT APPLY THIS PROCESS TO ALUMINUM OR TITANIUM ALLOYS.

<u>CAUTION:</u> THIS CLEANING PROCESS REQUIRES MASKING OF SEAL TEETH ALUMINUM OXIDE TOPCOAT UNLESS OTHERWISE SPECIFIED PER APPLICABLE REPAIR DOCUMENT.

- A. This cleaning method is a hot-tank process which is effective for removing rust, stripping paint, and general cleaning of ferrous and high-temperature alloy jet engine parts.
- NOTE: If the seal teeth aluminum oxide topcoat will be stripped and replaced before the part is returned to service, then the masking is not required.

NOTE: Ultrasonic agitation of the solution(s) can be used to increase the cleaning efficiency. Refer to Subtask 70-21-06-110-535 for process details.

2. <u>Equipment</u>.

Subtask 70-21-06-110-041

- A. The following equipment is required for the application of this process.
  - (1) Safety equipment and devices which are standard equipment in surface treatment shops such as: eye bath, emergency showers, protective clothing against electroplating products and means for neutralizing acid or alkaline splashing.
  - (2) Processing plant for neutralizing waste and used solutions.
  - (3) Efficient ventilation system for extracting and neutralizing vapors.
  - (4) An alkaline degreasing tank made of stainless steel with a heating coil capable of heating the solution to 210°F (99°C).
  - (5) A water rinse tank made from stainless steel and a spray gun, used after the alkaline

GE PROPRIETARY INFORMATION - Not to be used, disclosed to others or reproduced without the express written consent of GE. Technical data is considered ITAR and/or EAR controlled; transfer of this data to a Non-US Person, without USG authorization, is strictly prohibited.

degreasing.

(6) A hot water rinse tank made from stainless steel (or a carbon steel tank with polypropylene lining) that can increase the temperature of the solution to 200°F (93°C).

#### 3. <u>Materials.</u>

Subtask 70-21-06-110-042

Alkaline Degreasing/Rust Removing Solution - Table 1						
Solution	No.	Operating Temperature °F (°C)				
Ardrox 185 or Ardrox 185L	S1024	180-200 (82-93)				
Ardrox 1618	S1189	180-200 (82-93)				
Turco 4181, Turco 4181-L or Turco 4181-GL	S1006	180-200 (82-93)				
MagChem HDP-2888	S1017	180-200 (82-93)				
Cee-Bee J-84A or Cee-Bee J-84AL	S1026	180-200 (82-93)				
MagChem HDL-202	S1150	180-200 (82-93)				
Eldorado HTP-1150	S1161	180-200 (82-93)				
Eldorado HTP-1150L	S1162	180-200 (82-93)				
Applied 5-840	S1176	180-200 (82-93)				
Millennium	S1218	max. 120 (48)				

#### 4. Procedure.

Subtask 70-21-06-110-043

- A. In case of excessive dirt, pre-clean the part. Refer to TASK 70-21-01-110-001 (70-21-01, Cleaning Method No. 1 Solvent Degreasing) or TASK 70-21-22-110-042 (70-21-22, Cleaning Method No. 22 Light Duty Aqueous Cleaning (method 1)).
- WARNING: ALKALINE SOLUTIONS ARE VERY ACTIVE AND CAUSE SERIOUS BURNS. AVOID CONTACT WITH SKIN, EYES, AND CLOTHING. IF CONTACT OCCURS, WASH IMMEDIATELY WITH ABUNDANT QUANTITY OF WATER. AVOID BREATHING VAPORS.

WARNING: OPERATOR SHOULD WEAR FACE SHIELD, GLOVES, PROTECTIVE CLOTHING, AND PROTECTIVE SHOES.

B. Immerse the part in a tank containing one of the alkaline degreasing/rust removing solutions and maintain at the specified temperature. The solutions are listed in Subtask 70-21-06-110-042, Materials.

Duration: 15 to 60 minutes.

- C. Rinse by spraying with a water jet and by immersion in water at room temperature.
- D. If the parts are still not clean, you can do Steps 4.B. thru 4.C. again provided that the total time in the alkaline degreasing/rust removing solution does not exceed 60 minutes.
- E. Rinse by immersion in hot water at minimum 150°F (66°C).
- WARNING: WHEN USING COMPRESSED AIR FOR CLEANING, COOLING, OR DRYING, DO NOT EXCEED 30 PSIG (207 KPA). WEAR EYE PROTECTION AND DO NOT DIRECT COMPRESSED AIR AT SELF OR OTHERS.
- <u>CAUTION:</u> PARTS MUST BE THOROUGHLY DRY PRIOR TO FPI INSPECTION. WATER ON THE PARTS MAY DEGRADE THE SENSITIVITY OF THE PROCESS, ESPECIALLY FOR THE WATER WASHABLE PENETRANT PROCESS.
- F. Dry the part by one of the following two methods.
  - (1) Flash dry the part as follows:
    - (a) Keep the part submerged until the part reaches a temperature sufficient to provide for flash drying.
    - NOTE: The time required will vary with part size, water temperature and tank size. Proper flash drying is indicated by seeing the water on the surface of a part start to "flash" or "whisk" off as the part is being removed from the hot water tank.
    - (b) Remove the part from the water. The part will flash dry as soon as it is removed from the water. Use repositioning, suction, blotting with a clean, absorbent material, or by blowing off with an oil and water filtered shop air gun to remove excess water.
  - (2) You can substitute drying the part in an air re-circulating oven for the dwell time in the hot water.
    - (a) Remove the part from the water. You can remove excess water by repositioning, suction, blotting with a clean absorbent material, or blowing the water off with an oil and water filtered shop air gun.
    - (b) Move the part to the oven and dry at  $200^{\circ}F \pm 25^{\circ}F$  (93°C  $\pm 14^{\circ}C$ ) until the part reaches the oven temperature and all traces of surface water are removed.
- G. If parts are still not clean, repeat Steps 4.B. thru 4.D.
- H. Dry using clean, dry air.
- 5. Quality Assurance.

Subtask 70-21-06-110-044

- A. Visually check the part for cleanliness.
- 6. <u>Ultrasonic Agitation of the Solution(s).</u>

Subtask 70-21-06-110-535

CAUTION: ULTRASONIC CLEANING AND RINSING MUST NOT BE APPLIED TO SOFT METALS SUCH AS ALUMINUM AND MAGNESIUM WITHOUT SPECIFIC APPROVAL IN THE PROCESS DOCUMENT. SPECIAL TESTING CAN BE NECESSARY FOR THESE MATERIALS.

CAUTION: OTHER AGITATION METHODS (LIKE AIR AGITATION, MAGNETIC AGITATION, ETC) MUST NOT BE USED DURING ULTRASONIC AGITATION PROCESS OR DAMAGE TO THE PART CAN OCCUR.

A. Ultrasonic agitation of the solution can be used to increase the efficiency of the cleaning process. This subtask gives process parameters for ultrasonic agitation. Refer also to Subtask

- 70-21-06-110-535 for safety precautions and general information.
- **NOTE:** Usually, the lower the frequency is, the stronger the cavitation action and cleaning efficiency is.
- NOTE: Ultrasonic agitation process can only be used for approved part(s). Approval for use of "ultrasonic agitation" shall be obtained from design/life cycle engineer of the part. Submit data in Subtask 70-21-06-110-535 and listed in Sheet 1. Further information communicate with GE AVIATION Customer Support Center.
- B. Processing tank with temperature control.
  - (1) The ultrasonic tank should be made of stainless steel and be equipped with either a heat exchanger or heating coil capable of controlling the working solution at the minimum and the maximum operating temperature established.
  - **NOTE:** The ultrasonic energy will tend to increase the temperature of the working bath. It must be taken in to consideration during monitoring the bath operating temperature ranges.
  - CAUTION: THE LIQUID IN THE ULTRASONIC UNIT MUST BE AT THE CORRECT WORKING DEPTH OR DAMAGE TO THE PARTS CAN OCCUR.
  - (2) The tank should be clearly labeled with the minimum operating level.
  - (3) The tank must be provided with an automatic timer interlock to shut off the ultrasonic equipment, a low solution level shut-off interlock, or with a minimum solution level marker. The tank should be identified and clearly labeled with the chemical contents, power density, frequency of the ultrasonic unit, and rated capacity in gallons (or liters).
- C. Generator requirements.
  - CAUTION: THE PARTS MUST NOT TOUCH THE TRANSDUCERS OR DAMAGE TO THE PARTS CAN OCCUR.
  - (1) The generator must be a fixed power rating and not be adjustable by the operator.
    - (a) The ultrasonic tank must be operated at a frequency between 25 and 80 kHz and shall be maximum 80 watts/gallons (21.1 watts per liter) power density.
    - (b) Transducers should be equipped with High Sweep Modulation capability for optimum cleaning efficiency. The sweep range should be 0.5 to  $4~\mathrm{kHz}$ .
    - NOTE: Cavitation meters/probes can be used for determination of tank properties.
- CAUTION: ULTRASONIC ENERGY WILL TEND TO INCREASE THE TEMPERATURE OF THE WORKING BATH, SO COOLING AS WELL AS HEATING CAPABILITY MAY BE NECESSARY. THE BATH OPERATING TEMPERATURE RANGES MUST BE CAREFULLY MONITORED.
- CAUTION: IT IS CRITICAL THAT THERE BE NO DIRECT MECHANICAL CONTACT BETWEEN THE ENGINE COMPONENT AND THE ULTRASONIC TRANSDUCER OR THE TANK. IF CONTACT OCCURS, HOLD THE PARTS AND CONSULT YOUR GE AVIATION REPRESENTATIVE FOR DISPOSITION.
- CAUTION: NEW AND COLD SOLUTIONS ARE TO BE DEGASSED PRIOR TO USE. THE TIME REQUIRED FOR DEGASSING SOLUTIONS WILL VARY DEPENDING ON THE TANK CAPACITY AND TEMPERATURE. THIRTY MINUTES IS USUALLY ADEQUATE TO DEGAS HEATED SOLUTIONS. IF THE SOLUTION HAS BEEN PREVIOUSLY DEGASSED BUT HAS BEEN ALLOWED TO COOL, 10 MINUTES IS USUALLY ADEQUATE TO DEGAS THE HEATED SOLUTION. EVIDENCE THAT A SOLUTION HAS BEEN ADEQUATELY DEGASSED IS WHEN AIR BUBBLES ARE NO LONGER BEING GENERATED BY THE LIQUID.
- D. Ultrasonic cleaning units must be checked for operating efficiency periodically, at a frequency depending on the usage, with a suitable method.
  - (1) Alternative Method:
    - (a) Use Heavy Duty Reynolds Aluminum Foil, or similar aluminum foil, 0.009 inch (0.023 centimeter) in thickness.
    - (b) Fabricate a foil sheet such that when placed vertically in the tank, foil spans the entire depth and the longest width of tank dimensions.
      - Bend edges of foil for rigidity (to prevent foil from bending when placing in solution/tank).
      - 2 If the span is too large for one sheet of foil, fabricate a stainless-steel light rod framework (such as welding rod) to attach the foil.
    - (c) Cleaning solution should be that as specified by the cleaning procedure. If the cleaning solution reacts with aluminum foil, water should be used.
    - **NOTE:** Initial temperature should be set to minimum to avoid any possible overheating of the solution caused by ultrasonic agitation.
    - <u>WARNING:</u> OPERATOR SHOULD WEAR FACE SHIELD, GLOVES, PROTECTIVE CLOTHING AND PROTECTIVE SHOES. <u>CAUTION:</u> ALUMINUM FOIL MAY REACT WITH CLEANING SOLUTION. USE WATER FOR SUCH CASES. <u>CAUTION:</u> ALUMINUM FOIL REACTS WITH ALKALINE SOLUTION.
    - (d) Degas cleaning solution in an ultrasonic tank for the required time (approximately 15 minutes) for maximum cavitation intensity.
    - (e) Immerse aluminum foil vertically into an ultrasonic tank slow and gently to minimize disturbing the sheet.
    - (f) Keep aluminum foil immersed in an active ultrasonic tank for one minute.
    - (g) Remove aluminum foil sheet vertically slow and gently to minimize disturbing the sheet. **NOTE:** The ultrasonic generator must be OFF during immersion and removal of foil.
  - (2) Alternative Method:
    - (a) If contamination by aluminum foil debris is not desired, the foil must be immersed in a suitability sized glass beaker that contains water.
    - (b) Degas the water in the beaker for 10 minutes for maximum cavitation intensity.
    - (c) Put the beaker in the solution and minimize the attenuation of the ultrasonic vibrations.
    - (d) Keep the foil immersed in the water in the beaker for 90 seconds of operation. **NOTE:** Repeat the test several times with new foil for each different positions in the

working zone. The number of times will depend on the size of the tank.

- (3) Acceptance Criteria. Foil must have a complete and even distribution pattern of pockmarks or indentations throughout entire sheet. Some tiny through holes may be created, and are acceptable if there is a relatively even distribution of these holes.
- (4) Rejection. If foil patterns include lack of or light pockmark patters, inconsistent and uneven pockmark distribution, and large through hole(s) in localized areas bath. If the previous condition are present, the bath cannot be used.
- (5) Foil test must be repeated after:
  - (a) The first installation, upgrades, or repair of ultrasonic equipment (comprised of transducers, controls, wiring, power unit)
  - (b) The first installation of the immersion tank.
  - (c) Repair on the wetted walls of the immersion tank.
- E. Fixture Requirements.
  - (1) The parts must be suspended in the tank completely independent of the tank sidewalls, tank bottom, or transducer surface.
  - (2) The fixtures can be hung from the lip of the tank if the points of contact are insulated or dampened from the ultrasonic transducer or the tank.
  - (3) Parts should be placed at least 2 inches (50.8 mm) from the ultrasonic transducers or the tank walls and bottom. Parts shall never be closer than 1 inch (25.4 mm) from the tank walls and bottom. They shall be submerged at least 1 inch (25.4 mm) below the top of the solution. If the parts have holes and/or cavities, the parts must be rotated to be sure that all holes and/or cavities are filled with cleaning solution and all the air is removed.
  - (4) Part-to-part or metal (rack)-to-part contact during ultrasonic cleaning is not permitted. If more than one part is cleaned at a time, it is recommended that you use fixtures to put the parts in position so that it is impossible for the parts to touch one another during the ultrasonic agitation.
  - (5) Fixtures should be designed to maximize mesh opening size.
  - (6) Fixtures should be fabricated from plastic or plastic-coated metal to minimize the risk of part damage at the point of contact with the fixture.
- F. Deleted.

<u>CAUTION:</u> MAXIMUM IMMERSION TIME IS ESTABLISHED DURING QUALIFICATION. ENSURE MAXIMUM EXPOSURE TIME AS PER QUALIFICATION IS NOT EXCEEDED.

- G. This paragraph contains the substantiation requirements for components cleaned by ultrasonic agitation process. Substantiation by part number is required.
  - (1) For every new part to be cleaned with the assistance of ultrasonic, the 1st article must be run 4X (4 times) the maximum time based on the historical time needed to clean the part using the standard cleaning process. This should include the time in each tank of the cleaning process that is to be equipped with ultrasonic capability. All standard non-destructive inspections required for the part should be completed before and shall be completed after the 4X cleaning test to assure no damage or cracks are caused by the cleaning process.
  - (2) A demonstration of the cleaning procedure is necessary on a stock loss coupon of the alloy in question. This demonstration must use 4X (4 times) the maximum time based on the historical time needed to clean the part using the standard cleaning process. This should include the time in each tank of the cleaning process that is to be equipped with ultrasonic capability, maximum temperature and concentration of solution developed for the application. Stock loss testing should be performed according to ARP1755.
  - (3) Filtration and cleanliness requirements should be established for the cleaning solutions.
- \* \* \* FOR ALL

	DESCRIPTION OF TANK	LENGTH, WIDTH, HEIGHT (cm/inch)	
MENT	DIMENSIONS	ACTUAL VOLUME OF SOLUTION (gallons/liters)	
EQUIPMENT	DESCRIPTION OF GENERATOR AND FREQUENCY USED	WATTS/GALLON (watts/liter)	
	DESCRIPTION OF HIGH-END MODULATION (SWEEP FREQUENCY) RANGE	kHz	
	PROCESS	SPM ATA NUMBER OF THE PROCESS	
	SOLUTION CONCENTRATION	SOLUTION CODE	
PROCESS	PROCESS TIME IN TANK	minutes	
_	SOLUTION TEMPERATURE RANGE	°C/°F	
	FIXTURE IDENTIFICATION DESCRIPTION OF HOW SUPPORTED		
PART	P/N SUBJECTED TO THE ULTRASONIC CLEANING	MENTION THE PART FINISH OF THE PART (E.G. COATING)	
TIBILITY	STOCK LOSS CALCULATED	ACCORDING TO ARP1755 TO SUBJECTED PART BASE MATERIALS (inch)	
COMPATIBILITY	NDT RESULTS	VIBE ANALYSIS RESULTS (IF EXISTS) OR NDT RESULTS PART REQUIRED	

5051760-00

Figure 1 Cleaning Process Control Sheet for Ultrasonic Agitation

GE Designated: - CONFIDENTIAL Subject to the restrictions on the media